

## **Eni Coro WMO 8**

**Eni Coro WMO 8** is a water miscible corrosion protection fluid based on mineral oil. It contains emulsifiers and corrosion protection additives and forms a slightly oily, non-sticky film after the application.

## **Characteristics (typical figures):**

| Eni CORO WMO 8           |     | Unit         | Test method   |
|--------------------------|-----|--------------|---------------|
| Colour                   | 5   |              |               |
| Density at 15°C          | 921 | kg/m³        | DIN 51 757    |
| Viscosity at 20°C        | 110 | mm²/s        | DIN 51 562    |
| Viscosity at 40°C        | 60  | mm²/s        | DIN 51 562    |
| pH value of the emulsion | 8,5 | 10%          | DIN 51 369    |
| Condensation climate     | > 8 | (10%) cycles | DIN 50 017    |
| Salt spray test          | 48  | (10%) h      | DIN 50 021 SS |

## **Properties and Performance:**

- forms a slightly oily, non-sticky protection film
- excellent emulsion stability
- easily removable with conventional solvents or aqueous alkaline cleaning agents.

## **Applications:**

**Eni Coro WMO 8** is best suitable for the preservation of blank and phosphated surfaces.

Before application **Eni Coro WMO 8** is mixed with water in proportion of ingredients about 10 to 30% and applied by dipping at about 70°C. The product is a water hazardous liquid.

For specific technical questions please contact our technical department. Get information in reference to our training seminar about the subject cooling lubricants.